

THERMOWOOL FAS EXTRA 90 heat-insulating mineral wool boards

Production in compliance with the standard EN 13162.

MW-EN 13162-T5- DS (70,-)-DS(23,90)-CS(10)15-TR5-PL(5)50 -WS-
WL(P)-MU1 RtF: A1

MANUFACTURER: LLC «Plant «TECHNO» 18018 Ukraine, Cherkassy,
Rizdvyana Street 300.

ORIGIN: Ukraine



Non-flammable stone wool slabs made of basaltic and gabbroic rocks

Product Description

THERMOWOOL FAS EXTRA 90 is non-flammable, hydrophobized heat- and sound-insulating slabs made of mineral wool based on the basalt group rocks.

Scope of application:

THERMOWOOL FAS EXTRA 90 slabs are intended for use in civil and industrial construction as thermal and sound insulation in systems of external wall insulation with a protective and decorative layer of fine plaster.

Storage:

Slabs should be stored packed and stacked on pallets divided by types and sizes. During the entire storage period, the material must be protected from atmospheric precipitation. The height of the stack of slabs should not exceed 3 m upon storage.

Packaging Details:

Polyethylene shrink wrap is used for packaging. The method of wrapping and fixing a packaging material must ensure the reliable and strong packaging of slabs, their protection during loading and unloading operations, transportation and storage.

Technical Characteristics

ESSENTIAL CHARACTERISTICS	PERFORMANCE	HARMONIZED TECHNICAL SPECIFICATION
Declared thermal conductivity at 10 °C, λ_D , W/m ² K	0,036	EN 13162:2012 + A1:2015
Limit deviations length/width, mm	$\pm 2/\pm 1,5$ %	
Limit deviations of thickness, mm	T5	
Thickness, (with increments of 10 mm), mm	50-200	
Deviation from squareness, mm/m	< 5	
Deviation from flatness, mm	< 6	
Compressive stress at 10% deformation, kPa	CS(10)15	
Tensile strength perpendicular to faces, kPa	TR5	
Point Load, N	PL(5)50	
Dimensional stability, %:		
- at specified temperature	DS(70,-) less than 1	
- under specified temperature (23oC) and humidity conditions (90%R.H.)	DS(23,90) less than 1	
Reaction to fire, euroclass	A1	
Water Absorption during Short/ Longterm Immersion kg/m ²	WS less than 1 WL(P) less than 3	
Water vapour transmission, MU	MU1	
Dangerous substances	Does not include dangerous substances	